

	CLEANING PROCEDURES FOR FALLING-FILM EVAPORATORS (FFE) IN CANE SUGAR FACTORIES		
	MECHANICAL		CHEMICAL
	High pressure water-jet system	Rädler-Tube-Cleaning (RTC)	
Procedure	 deposits are removed by using high-pressure cleaning with the aid of water. cleaning lance is guided manually, with or without machine guidance. high-pressure pump is permanently installed at 0 m. 	 deposits are ground down with a drill milling head corresponding to the inner diameter of the heating tube and removed using water cooling. drill milling head is 0.5 mm smaller in diameter than the heating tube. feed rate of the drill milling head is adjustable. drill milling head is guided manually within the machine guide. machine guide is mobile, can be mounted on the tube sheet 	 deposits are removed by using acids and/or lyes at temperatures in the range of 60°C to 80°C. inhibitor must be added to prevent corrosion of the evaporator material. in between, the FFE must be rinsed repeatedly with hot water. chemicals must be pumped from containers into the FFE. For this purpose, they are often added on the suction side of the circulation pump.
Consumption of water and chemicals	 approx. 40 L/min, depending on supplier → approx. 76 m³ at 1900 tubes (corresponding to: 2000 m²/ 8 m) 	 max. 9 L/min → approx. 17 m³ at 1900 tubes (corresponding to: 2000 m²/ 8 m) 	 min. 20 m³ water for the acid solution (5 %) / FFE min. 20 m³ water for the caustic solution (6 %) / FFE → approx. 40 m³ / FFE
Operating pressure	up to 1000 bar, depending on supplier	• max. 8 bar	none that is in direct contact with a person
Duration of cleaning	 approx. 1 min / tube, depending on degree of incrustration 	approx. 1-1,5 minute(s) / 10 m tube, depending on degree of incrustration'	• approx. 20 h / FFE
	→ approx. 1 day for 1900 tubes / high pressure water-jet system	 → approx. 1,5 - 2 days for 1900 tubes / RTC-device → max. 4 devices can work at the same time, depending on the available space 	→ max. 1 day / FFE